

**Amendments to the Specification:**

Please replace the paragraph (45) with the following amended paragraph (45):

(45) The preferred aluminum powder 13 is manufactured by Eckart America L.P. of Louisville, KY. The Eckart Part Number is SDF 2-382. It is described as a

5 medium grade, dedusted, leafing aluminum flake powder with the following characteristics:

Nonvolatile Matter,

99% minimum 325 Mesh Retention,

2% maximum Average particle size,

10 16 micron ~~Surface Area~~ particle size,

1.06 square meters ~~per sq cm~~ per cubic cm,

Weight per Solid Gallon - 21.06 lbs per gallon,

Bulking Value - 0.047 gal/lb,

Teflon - 0.1 %,

15 Stoddard Solvent - 1% to 2%,

Stearic Acid - 1% to 2%.